



Grade slates into 3 or 4 groups of equal thickness.
 Sort slates in each group so that thin end of slates will be towards the ridge.
 Hole slates from the rear.
 Lay slates of equal thickness in the same course.
 Lay thicker slates at eaves, thinner towards the ridge.

CEMBRIT LIMITED
 MANSARD ROOF TYPICAL DETAIL
 508x254 GLENDYNE (NATURAL SLATE)
 DRG No. 620 H62/105 and 280